





## INTRODUCING OUR NEW PRODUCT NOMENCLATURE

Bisalloy Steels has recently introduced a new product nomenclature. The following table details the grade equivalents.

Note: Only the designation has changed – not the product

Previous Name	New Name
BISPLATE® 60	BISALLOY® Structural 60 steel
BISPLATE® 70	BISALLOY® Structural 70 steel
BISPLATE® 80	BISALLOY® Structural 80 steel
BISPLATE® 100	BISALLOY® Structural 100 steel
BISPLATE® 80PV	BISALLOY® Structural 80 Pressure Vessel steel
BISPLATE® 320	BISALLOY® Wear 320 steel
BISPLATE® 400	BISALLOY® Wear 400 steel
BISPLATE® 450	BISALLOY® Wear 450 steel
BISPLATE® 500	BISALLOY® Wear 500 steel
BISPLATE® 600	BISALLOY® Wear 600 steel
BISPLATE® HIA - Class 1	BISALLOY® Armour RHA300 steel
BISPLATE® HIA - Class 2	BISALLOY® Armour RHA360 steel
BISPLATE® HTA	BISALLOY® Armour HTA400 steel
BISPLATE® UHT	BISALLOY® Armour UHT440 steel
BISPLATE® HHA	BISALLOY® Armour HHA500 steel
BISPLATE® UHH	BISALLOY® Armour UHH600 steel



## WELDING OF BISALLOY® QUENCHED AND TEMPERED STEELS

### General Information

All grades of BISALLOY® steel can be readily welded using any of the conventional low hydrogen welding processes.

Their low carbon content and carefully balanced, but relatively small additions of alloying elements (Mn, Cr, Mo, B) ensures good weldability, in addition to the advantages of high strength, impact toughness and high hardness.

### HYDROGEN CONTROL

To ensure adequate welding of BISALLOY® steel, it is necessary to be more mindful of the levels of hydrogen, preheat temperatures and arc energy inputs in order to minimise the hardening and maintain the properties of the weld Heat Affected Zone (HAZ).

Particular attention must be paid to the control of hydrogen content to minimise the risk of weld and HAZ cracking. Weld hydrogen content is minimised by careful attention to the cleanliness and dryness of the joint preparations and the use of hydrogen controlled welding consumables. Recommendations on the correct storage and handling of consumables may be obtained from welding consumable manufacturers, for instance the use of "Hot Boxes" for storage and reconditioning are required when using manual metal arc welding electrodes. Refer WTIA Tech Note 3 for further guidance.

### HEAT AFFECTED ZONE PROPERTY CONTROL

The HAZ, a region directly adjacent to the weld, experiences a thermal cycle ranging from unaffected parent plate to near melting at the fusion boundary.

The properties of this zone are determined by the steel composition as well as the cooling rate.

Table 1:

BISALLOY® steel grade	PLATE THICKNESS (mm)	CARBON EQUIVALENT (IIW) TYPICAL	CET TYPICAL AVERAGE
60, 70, 80, 100, 320, 400	5 - <16	0.40	0.29
60, 70, 80, 320, 400	16 - <32	0.50	0.35
60, 70, 80, 320, 400	≥32 - 80	0.54	0.32
60, 70, 80, 320, 400	81 - 100	0.58	0.34
450	6 - 20	0.46	0.30
	25 - 50	0.58	0.36
500	8 - 100	0.62	0.42
600	12 - 50	0.75	0.52

## STEEL COMPOSITION

BISALLOY® Steel grades and chemical compositions may be divided into categories based on Carbon Equivalent and CET as seen in Table 1:

Notes:

$$1. \quad \text{C.E. (IIW)} = C + \frac{\text{Mn}}{6} + \frac{\text{Cr} + \text{Mo} + \text{V}}{5} + \frac{\text{Cu} + \text{Ni}}{15}$$

$$2. \quad \text{CET} = C + \frac{\text{Mn} + \text{Mo}}{10} + \frac{\text{Cr} + \text{Cu}}{20} + \frac{\text{Ni}}{40}$$

These categories give an indication of the degree of care required in the proper selection of welding preheat/heat inputs.

## COOLING RATE

Limitations on both preheat and heat input are necessary to ensure that the HAZ cools at an appropriate rate and that the correct hardness and microstructure are achieved. Too slow a cooling rate can result in a soft HAZ and thus a loss of tensile and fracture toughness properties. Too rapid a cooling rate produces a hard HAZ which may cause loss of ductility.

Cooling is controlled by a balance between preheat and heat input for a particular plate thickness and joint configuration.

## PREHEAT/ HEAT INPUT

The preheat/heat input recommendations outlined in tables 2 and 3 will ensure that the cooling rate of the HAZ is satisfactory.

## RECOMMENDED PREHEAT/INTERPASS TEMPERATURES (°C) FOR BISALLOY® STEEL

Table 2:

BISALLOY® steel grade	JOINT COMBINED THICKNESS ( $t_1 + t_2 + t_3$ ) (mm)				
	<30	≥30 ≥40	>40 <50	≥50 <100	≥100
<b>Minimum Preheat Temperature °C High Strength Structural Grades</b>					
60 (AS 3597 Grade 500)	Nil*	50	50	75	140
70 (AS 3597 Grade 600)	Nil*	50	50	75	140
80 (AS 3597 Grade 700)	Nil*	50	50	75	140
100 (AS3597 Grade 900)	Nil*	50	50	75	140
<b>Minimum Preheat Temp°C Abrasion Resistant Grades</b>					
320	Nil*	75	75	125	150
400	Nil*	75	75	125	150
450	Nil*	Nil*	100	125 **	**
500	100	150	150	150	**
600	150	150	150	**	**
<b>Maximum Interpass Temperature °C</b>					
80 - 450 Grades	150	150	175	200	220
500 Grade	150	175	175	200	220
600 Grade	150	175	175	220	220

\* Chill must be removed from plates prior to welding.

\*\* Refer to Bisalloy Steels for availability, preheat/interpass requirements.

\*\*\*A reduced 100°C min preheat can be used for product ≥50 – 60 JCT

Note that under rigid weld joint restraint or high ambient humidity conditions preheating temperature should be increased by 25°C

## PERMISSIBLE HEAT INPUT (KJ/MM) FOR BISALLOY® STEEL

Table 3:

Welding Process	MAXIMUM PLATE THICKNESS IN JOINT (mm)			
	≤40	>40 ≤60	>60 ≤100	>100
MMAW	1.25-2.5	1.25-3.5	1.5-4.5	1.5-5.0
GMAW	1.0-2.5	1.0-3.5	1.5-4.5	1.5-5.0
FCAW	0.8-2.5	0.8-3.5	1.5-4.5	1.5-5.0
SAW	1.0-2.5	1.0-3.5	1.5-4.5	1.5-5.0

$$\text{Heat Input (kJ/mm)} = \frac{\text{Volts} \times \text{Amps} \times 0.06}{\text{Travel Speed (mm/minute)}}$$

Note: For thicknesses up to 12 mm in structural grades, the maximum arc energy may need to be limited to 1.5 KJ/mm maximum in specific applications

## WELDING CONSUMABLES

### Welding Consumable Selection Guide for BISALLOY® steel (AS Classifications)

Table 4a:

BISALLOY® steel grade		MAXIMUM PLATE THICKNESS IN JOINT (mm)				
		BISALLOY® Structural 60 steel	BISALLOY® Structural 70 steel	BISALLOY® Structural 80 steel	BISALLOY® Wear 100, 320, 400, 450 & 500 steel	
<b>MMAW Consumables* Warning: Only use Hydrogen Controlled consumables</b>	Strength Level	Matching	E55XX/E62XX+	E69XX~	E76XX	N.R.
		Lower	E49XX	E55XX	E55XX/E62XX+	E55XX
		Lower	E49XX	E49XX	E49XX	E49XX
	Hardness	Matching	N.R.	N.R.	N.R.	1430-AX, 1855-AX^
<b>GMAW Consumables**</b>	Strength Level	Matching	W55XX/W62XX+	W69XX+	W76XX	N.R.
		Lower	W50XX	W55XX	W62XX/W69XX	W55XX
		Lower	W50XX	W50XX	W55XX.X	W50XX
	Hardness	Matching	N.R.	N.R.	N.R.	1855-BX^
<b>FCAW Consumables***</b>	Strength Level	Matching	B T 55X/B T 62X+	B T 69X~	B T 76X	N.R.
		Lower	B T 49X	B T 62X	B T 62X	B T 55X
		Lower	B T 49X	B T 55X	B T 55X	B T 49X
	Hardness	Matching	N.R.	N.R.	N.R.	1430-BX, 1855-BX, 1860-BX^
<b>SAW Consumables****</b>	Strength Level	Matching	W55XX/W62XX+	W69XX~	W76XX	N.R.
		Lower	W50XX	W50XX	W50XX	W50XX
		Lower	W50XX	W40XX	W40XX	W40XX
	Hardness	Matching	N.R.	N.R.	N.R.	1855-BX^

Table 4a courtesy of WT/A (Tech. Note 15)

#### Notes:

*	MMAW - AS/NZS 4855 consumable classification	+	E62XX and W62XX type consumables overmatch the strength requirements but may be used
**	GMAW - AS2717.1 consumable classification	~	These Consumables may be difficult to obtain. In some cases E62XX, W62XX or B T 62X consumables may be substituted, otherwise use E76XX, W76XX or B T 76X types
***	FCAW - AS/NZS17632 and AS/NZS18276 consumable classification	^	AS2576 and WTIA TN 4 Classifications
****	SAW - AS1858.1 and AS1858.2 consumable classification	N.R.	Not Recommended
X	A Variable - any value allowed by the relevant standard may be acceptable provided that the consumable is hydrogen controlled (ie low hydrogen)		

## WELDING CONSUMABLES

### Welding Consumable Selection Guide for BISALLOY® steel (AWS Classifications)

Table 4b:

BISALLOY® steel grade		MAXIMUM PLATE THICKNESS IN JOINT (mm)				
		BISALLOY® Structural 60 steel	BISALLOY® Structural 70 steel	BISALLOY® Structural 80 steel	BISALLOY® Wear 100, 320, 400, 450 & 500 steel	
<b>MMAW Consumables*</b> <b>Warning: Only use Hydrogen Controlled consumables</b>	Strength Level	Matching	E80XX/E90XX+	E100XX~	E110XX	N.R.
		Lower	E70XX	E80XX	E80XX/E90XX	E80XX
		Lower	E70XX	E70XX	E70XX	E70XX
	Hardness	Matching	N.R.	N.R.	N.R.	1430-AX, 1855-AX^
<b>GMAW Consumables**</b>	Strength Level	Matching	ER80S-X/ER90S-X+	ER100S-X~	ER110S-X	N.R.
		Lower	ER70S-X	ER80S-X	ER90S-X/ER100S-X	ER80S-X
		Lower	ER70S-X	ER70S-X	ER80S-X	ER70S-X
	Hardness	Matching	N.R.	N.R.	N.R.	1855-BX^
<b>FCAW Consumables***</b>	Strength Level	Matching	E8TX-X/E9TX-X+	E10TX-X~	E11TX-X	N.R.
		Lower	E7TX-X	E9TX-X	E9TX-X	E8TX-X
		Lower	E7TX-X	E8TX-X	E8TX-X	E7TX-X
	Hardness	Matching	N.R.	N.R.	N.R.	1430-BX, 1855-BX, 1860-BX^
<b>SAW Consumables****</b>	Strength Level	Matching	F8XX/F9XX+	F10XX~	F11XX	N.R.
		Lower	F7XX	F7XX	F7XX	F7XX
		Lower	F6XX	F6XX	F6XX	F6XX
	Hardness	Matching	N.R.	N.R.	N.R.	1855-BX^

Table 4b courtesy of WT/A (Tech. Note 15)

#### Notes:

*	MMAW – AWS A5.1-2004 and AWS A5.5 consumable classification	+	E90XX, ER90S, E9TX and F9XX type consumables overmatch the strength requirements but may be used
**	GMAW – AWS A5.18-2005 and AWS A5.28 consumable classification	~	These Consumables may be difficult to obtain. In some cases E90XX, ER90S, E9TX or F9XX type consumables may be substituted, otherwise use E110XX, ER110S, E11TX or F11XX types
***	FCAW – AWS A5.20-2005 and AWS A5.29 consumable classification	^	AS2576 WTIA TN 4 Classifications
****	SAW – AWS A5.17-1997 and AWS A5.23 consumable classification	N.R.	Not Recommended
X	A Variable - any value allowed by the relevant standard may be acceptable provided that the consumable is hydrogen controlled (ie low hydrogen)		

## WELDING CONSUMABLES

Welding Consumables suitable for matching strength, lower strength and matching hardness are readily available from a range of consumable manufacturers as per following tables 5 to 8.

### Welding Consumables for Manual Metal Arc Welding (MMAW)

Table 5:

Brands		BISALLOY® Structural 60 steel	BISALLOY® Structural 70 steel	BISALLOY® Structural 80 steel	BISALLOY® Wear 100, 320, 400, 450 & 500 steel
<b>CIGWELD</b>	M.S.	Alloycraft 90	Alloycraft 90 (under) Alloycraft 110 (over)	Alloycraft 110	N.R.
	L.S.	Ferrocrafft 61 Ferrocrafft 16 Twincoat	Ferrocrafft 61 Ferrocrafft 16 Twincoat	Ferrocrafft 61 Ferrocrafft 16 Twincoat	Ferrocrafft 61 Ferrocrafft 16 Twincoat
	M.H.	N.R.	N.R.	N.R.	Cobalarc 350, 650 or 750
<b>Lincoln</b>	M.S.	Conarc 70G	Conarc 80+	Conarc 80, Conarc 85+	N.R.
	L.S.	Conarc 49C, Easyarc 7018-1	Conarc 49C, Easyarc 7018-1	Conarc 49C, Easyarc 7018-1	Conarc 49C, Easyarc 7018-1
	M.H.	N.R.	N.R.	N.R.	N.R.
<b>W.I.A</b>	M.S.	N.R.	Weldwell PH118	Weldwell PH118	N.R.
	L.S.	Austarc 16TC, 18TC or Austarc 77	Austarc 16TC, 18TC or Austarc 77	N.R.	Austarc 16TC, 18TC or Austarc 77
	M.H.	N.R.	N.R.	N.R.	Abraso Cord 350, 700
<b>Specialised Welding Products (SWP) ^WAG = Welding Alloys Group</b>	M.S.	Metrode E9018-D1	Metrode E10018-D2	Metrode E11018-M	N.R.
	L.S.	WAG^ Speedarc 7018-1-E WAG^ Speedarc 7016-E	WAG^ Speedarc 7018-1-E WAG^ Speedarc 7016-E	WAG^ Speedarc 7018-1-E WAG^ Speedarc 7016-E	N.R.
	M.H.	N.R.	N.R.	N.R.	Metrode Methard 350 Metrode Methard 650 WAG^ Hardface 400-E WAG^ Hardface L-E
<b>SMENCO Eutectic Castolin</b>	M.S.	N.A.	N.A.	N.A.	N.R.
	L.S.	Eutectrode 66*66	Eutectrode 66*66	Eutectrode 66*66	Eutectrode 66*66
	M.H.	N.R.	N.R.	N.R.	N.R.
<b>ESAB</b>	M.S.	OK 74.70	OK 74.86	OK 75.75	N.A.
	L.S.	OK 48.08, OK 48.04	OK 48.08, OK 48.04	OK 48.08, OK 48.04	N.A.
	M.H.	N.R.	N.R.	N.R.	OK 83.28 (30 HRC) OK 83.50 (50-60 HRC)

M.S. Matching Strength  
L.S. Lower Strength  
M.H. Matching Hardness  
N.R. Not Recommended  
N.A. Not Available

N.B. Consumables in brackets will match mechanical property requirements in the majority of instances as per manufacturer's recommendations and where the appropriate weld procedure is applied. Weld Qualification procedures should be carried out to establish actual Weld metal properties.  
+ Overmatching strength



## WELDING CONSUMABLES

### Welding Consumables for Gas Metal Arc Welding (GMAW)

Table 6:

Brands		BISALLOY® Structural 60 steel	BISALLOY® Structural 70 steel	BISALLOY® Structural 80 steel	BISALLOY® Wear 100, 320, 400, 450 & 500 steel
<b>CIGWELD</b>	M.S.	Autocraft MnMo	Autocraft MnMo (Under) Autocraft NiCrMo (Over)	Autocraft NiCrMo	N.R.
	L.S.	Autocraft LW1 or Autocraft LW1-6	Autocraft LW1 or Autocraft LW1-6	Autocraft LW1 or Autocraft LW1-6	Autocraft LW1 or Autocraft LW1-6
	M.H.	N.R.	N.R.	N.R.	Autocraft HF650
<b>Lincoln</b>	M.S.	LNM Ni1	LNM Ni1 (UM)	LNM MoNiVa	N.R.
	L.S.	UltraMag S4 UltraMag S6**	UltraMag S4 UltraMag S6**	UltraMag S4 UltraMag S6**	UltraMag S4 UltraMag S6**
	M.H.	N.R.	N.R.	N.R.	N.R.
<b>W.I.A</b>	M.S.	Austmig ESD2/CO <sup>2</sup> or Mixed Gas	Austmig NiCrMo+	Austmig NiCrMo	N.R.
	L.S.	Austmig ES6/CO <sup>2</sup> or Mixed Gas	Austmig ES6/CO <sup>2</sup> or Mixed Gas	Austmig ES6/CO <sup>2</sup> or Mixed Gas	Austmig ES6/CO <sup>2</sup> or Mixed Gas
	M.H.	N.A.	N.A.	N.A.	TD600/CO <sup>2</sup> or Mixed Gas
<b>Specialised Welding Products (SWP)</b>	M.S.	SWP D2	SWP 110+	SWP 110	N.R.
	L.S.	SWP S6	SWP S6	SWP S6	N.R.
	M.H.	N.R.	N.R.	N.R.	SWP HF350 SWP HF600
<b>SMENCO/ Eutectic Castolin</b>	M.S.	AN45252+/ CO <sup>2</sup> or Mixed Gas	AN45252+/ CO <sup>2</sup> or Mixed Gas	AN45252/ CO <sup>2</sup> or Mixed Gas	N.R.
	L.S.	DO*65/CO <sup>2</sup> or Mixed Gas	DO*65/CO <sup>2</sup> or Mixed Gas	DO*65/CO <sup>2</sup> or Mixed Gas	DO*65/CO <sup>2</sup> or Mixed Gas
<b>ESAB</b>	M.S.	OK AristoRod 13.09 Mixed Gas	OK AristoRod 55 Mixed Gas	OK AristoRod 69 Mixed Gas	N.A.
	L.S.	OK AristoRod 12.50 CO <sup>2</sup> or Mixed Gas	OK AristoRod 12.50 CO <sup>2</sup> or Mixed Gas	OK AristoRod 12.50 CO <sup>2</sup> or Mixed Gas	N.A.
	M.H.	N.R.	N.R.	N.R.	OK AutoRod 13.89 (30-40HRC) OK AutoRod 13.90 (50-60HRC)

M.S. Matching Strength  
L.S. Lower Strength  
M.H. Matching Hardness  
N.R. Not Recommended  
N.A. Not Available

N.B. Consumables in brackets will match mechanical property requirements in the majority of instances as per manufacturer's recommendations and where the appropriate weld procedure is applied. Weld Qualification procedures should be carried out to establish actual Weld metal properties.  
+ Overmatching strength  
\*\* CO<sub>2</sub> or mixed gas

## WELDING CONSUMABLES

### Welding Consumables for Flux Cored Arc Welding (FCAW)

Table 7:

Brands		BISALLOY® Structural 60 steel	BISALLOY® Structural 70 steel	BISALLOY® Structural 80 steel	BISALLOY® Wear 100, 320, 400, 450 & 500 steel
<b>CIGWELD/ STOODY</b>	M.S. Seamless	Verticor 91K2 H4	Verticor 91K2 H4 (Under) ***Verticor 111K3 H4 (Over) Tensicor 110TXP H4 (Over) Metalcor 110 H4 (Over)	***Verticor 111K3 H4 Tensicor 110TXP H4 Metalcor 110 H4	N.R.
	L.S. Seamless (E6XT-X)	Verticor XP LT H4	Verticor XP LT H4	Verticor XP LT H4	Verticor XP LT H4
	L.S. Seamless	Verticor 3XP H4, Verticor 5XP H4, Metalcor 5 H4, Verticor 81Ni1 H4	Verticor 3XP H4, Verticor 5XP H4, Metalcor 5 H4, Verticor 81Ni1 H4	Verticor 3XP H4, Verticor 5XP H4, Metalcor 5 H4, Verticor 81Ni1 H4	Verticor 3XP H4, Verticor 5XP H4, Metalcor 5 H4, Verticor 81Ni1 H4
	L.S. Seamed	Verticor 3XP, Suprecor 5, Metalcor XP, Verticor 81Ni1 81Ni2	Verticor 3XP, Suprecor 5, Metalcor XP, Verticor 81Ni1 81Ni2	Verticor 3XP, Suprecor 5, Metalcor XP, Verticor 81Ni1 81Ni2	Verticor 3XP, Suprecor 5, Metalcor XP, Verticor 81Ni1 81Ni2
	L.S. Self Shielded	Shieldcor 8XP Shieldcor 8Ni	Shieldcor 8XP Shieldcor 8Ni	Shieldcor 8XP Shieldcor 8Ni	Shieldcor 8XP Shieldcor 8Ni
	M.H.	N.R.	N.R.	N.R.	Stoody Super Build-Up-G, Stoody 965-G, Stoody 965 AP-G
<b>Lincoln</b>	M.S.	Outershield 91Ni1-HSR	Outershield 91Ni1-HSR (UM)	Outershield 690-H	N.R.
	L.S.	Outershield 81Ni1, 71-MX, 71-CX Innershield NR-232, NR-233, NS-3M	Outershield 81Ni1, 71-MX, 71-CX Innershield NR-232, NR-233, NS-3M	Outershield 81Ni1, 71-MX, 71-CX Innershield NR-232, NR-233, NS-3M	Outershield 81Ni1, 71-MX, 71-CX Innershield NR-232, NR-233, NS-3M
	M.H.	N.R.	N.R.	N.R.	Lincore 33, Lincore 36LS, Lincore 55-G
<b>W.I.A/ Hobart Brothers</b>	M.S.	Austfil 81N1M/Mixed Gas, TM-71 HYD/CO2, TM-811N2/CO2 or Mixed Gas	FabCO 110K3M/Mixed Gas	FabCO 110K3M/Mixed Gas	N.R.
	L.S.	Austfil 71T-1/CO2, Austfil 70C-6M, 71T-1M/Mixed Gas, Formula XL-525/Mixed Gas, Fabshield 4, XLR-8	TM-991K2/CO2 or Mixed Gas, Austfil 81N1M/Mixed Gas, TM-71 HYD/CO2, TM-811N2/CO2 or Mixed Gas, Metalloy 80N1/Mixed Gas	TM-991K2/CO2 or Mixed Gas, Austfil 81N1M/Mixed Gas, TM-71 HYD/CO2, TM-811N2/CO2 or Mixed Gas, Metalloy 80N1/Mixed Gas	Austfil 70C-6M, 71T-1M, 81N1M/ Mixed Gas, Austfil 71T-1, TM-71, HYD/CO2 TM-811N2/CO2 or Mixed Gas, Metalloy 80N1/ Mixed Gas, Formula XL-525/Mixed Gas, Fabshield 4, XLR-8
	M.H.	N.A.	N.A.	N.A.	Vertiwear 600/Mixed Gas

Table 7 Continued:

Brands		BISALLOY® Structural 60 steel	BISALLOY® Structural 70 steel	BISALLOY® Structural 80 steel	BISALLOY® Wear 100, 320, 400, 450 & 500 steel
<b>SMENCO/ Eutectic Castolin</b>	M.S.	N.A.	N.A.	N.A.	N.A.
	L.S.	Teromatec OA2020	Teromatec OA2020	Teromatec OA2020	Teromatec OA2020
	M.H.	N.R.	N.R.	N.R.	N.R.
<b>Specialised Welding Products (SWP) ^WAG = Welding Alloys Group</b>	M.S.	WAG^ Robofil R Ni1+, WAG^ Robofil M Ni1, WAG^ Robofil B Ni1	WAG^ Robofil R 690+, WAG^ Robofil M 700, WAG^ Robofil B 700	WAG^ Robofil R690+, WAG^ Robofil M 700, WAG^ Robofil B 700	N.R.
	L.S.	WAG^ Robofil R 71+, WAG^ Robofil M 71, WAG^ Robofil B 71	WAG^ Robofil R 71+, WAG^ Robofil M 71, WAG^ Robofil B 71	WAG^ Robofil R 71+, WAG^ Robofil M 71, WAG^ Robofil B 71	N.R.
<b>ESAB</b>	M.S.	N.R.	N.R.	N.R.	WAG^ Robodur K350-G, WAG^ Robodur K450-G, WAG^ Robodur K600-G, WAG^ Hardface T-G, WAG^ Hardface P-G, WAG^ Hardface L-G, WAG^ Hardface LP-G
	M.S.	Dualshield II 80-Ni1H4 Mixed Gas	Dualshield T-100 CO2 Shielding Gas	Dualshield T-115 CO2 or Mixed Gas	N.A.
	L.S.	Dualshield 7100 Ultra Mixed Gas	Dualshield II 80-Ni1H4 Mixed Gas Dualshield 7100 Ultra Mixed Gas	Dualshield II 80-Ni1H4 Mixed Gas Dualshield 7100 Ultra Mixed Gas	N.A.
	M.H.	N.R.	N.R.	N.R.	OK Tubrodur 15.40 (30-40HRC) CO2, OK Tubrodur 15.52 (55-60 HRC ) CO2 or, Self Shielded

M.S. Matching Strength  
 L.S. Lower Strength  
 M.H. Matching Hardness  
 N.R. Not Recommended  
 N.A. Not Available

N.B. Consumables in brackets will match mechanical property requirements in the majority of instances as per manufacturer's recommendations and where the appropriate weld procedure is applied. Weld Qualification procedures should be carried out to establish actual Weld metal properties.  
 + Overmatching strength  
 \*\*\* Verticor 111K3 H4 not recommended for plate thickness over 20 mm

## WELDING CONSUMABLES

### Welding Consumables for Submerged Arc Welding (SAW)

Table 8:

Brands		BISALLOY® Structural 60 steel	BISALLOY® Structural 70 steel	BISALLOY® Structural 80 steel	BISALLOY® Wear 100, 320, 400, 450 & 500 steel
<b>CIGWELD</b>	M.S.	N.A.	Autocraft NiCrMo (Over)/ Satinarc 4	Autocraft NiCrMo/ Satinarc 4	N.R.
	L.S.	Autocraft SA1 SA2/ Satinarc 4 or 15	Autocraft SA1 SA2/ Satinarc 4 or 15	Autocraft SA1 SA2/ Satinarc 4 or 15	Autocraft SA1 SA2/ Satinarc 4 or 15
	M.H.	N.R.	N.R.	N.R.	Stoody 105 or 107/ Stoody S Flux
<b>Lincoln</b>	M.S.	Lincolnweld LA- 90/880M or 8500	Lincolnweld LAC-690 /880M /888+	Lincolnweld LAC-690 /880M /888	N.R.
	L.S.	L-60/L-61/ 761, 860, 960 Flux	L-60/L-61/ 761, 860, 960 Flux	L-60/L-61/ 761, 860, 960 Flux	L-60/L-61/ 761, 860, 960
	M.H.	N.R.	N.R.	LC25-S/880 Flux	Lincore 30-S, Lincore 42-S, Lincore50/880 or 802 Flux
<b>Specialised Welding Products (SWP) ^WAG = Welding Alloys Group</b>	M.S.	S3Ni1Mo Wire/BF10 Flux	S3Ni1Mo Wire/BF10 Flux	S3Ni2.5CrMo Wire/ BF10 Flux	N.R.
	L.S.	SWP EM12K Wire/ WAG^ WAF325 Flux	SWP EM12K Wire/WAG^ WAF325 Flux	SWP EM12K Wire/ WAG^ WAF325 Flux	N.R.
	M.H.	N.R.	N.R.	N.R.	WAG^ Hardface T-S Wire/ WAG^, WAF325 Flux, WAG^ Hardface P-S Wire/ WAG^, WAF325 Flux, WAG^ Hardface L-S/WAG^ WAF325 Flux
<b>ESAB</b>	M.S.	OK Tubrod 15.24S+ OK 10.62	OK Tubrod 13.43+ OK 10.62	OK Tubrod 15.27S+ OK 10.62	N.A.
	L.S.	OK 12.22/OK 10.71	OK 12.22/OK 10.71	OK 12.22/OK 10.71	N.A.
	M.H.	N.A.	N.A.	N.A.	N.A.

M.S. Matching Strength  
L.S. Lower Strength  
M.H. Matching Hardness  
N.R. Not Recommended  
N.A. Not Available

N.B. Consumables in brackets will match mechanical property requirements in the majority of instances as per manufacturer's recommendations and where the appropriate weld procedure is applied. Weld Qualification procedures should be carried out to establish actual Weld metal properties.  
+ Overmatching strength

## WELDING PROCEDURES

The specific effects of welding on weld joint properties in any practical situation will depend on many factors including the choice of consumables, total weld heat input, level of restraint, weld geometry and proximity of adjacent welds.

Guidance on weld procedures for specific applications may be sought from Bisalloy Steels technical staff or consumable suppliers.

## ARC STRIKES

Arc strikes outside the welded zone can result in cracks, particularly on dynamically loaded structures. All strikes should be made within the joint preparation.

## TACK WELDING

Tack welds require special care due to the abnormal stresses and high cooling rates experienced by the adjacent material.

The same preheat, heat input requirements should be employed and lower strength welding consumables considered.

## FILLET WELDING

Good fillet welding techniques are important in welding Q&T steels because often very high stresses are applied in service. It is essential that welds have good root penetration, be smooth, correctly contoured and well flared into the legs of the joined pieces. Lower strength consumables are suggested when design permits.

WTIA Tech. Note 15 provides guidance on correct procedures for fillet welding.

## REPAIR WORK

It is good practice to weld repair with lower strength consumables (low hydrogen type), since plate materials which have been highly stressed in service may tend to warp or distort slightly during welding and improved ductility may be required. In some situations, such as joints under restraint, joints subjected to impact/fatigue stresses, etc, special welding consumables may be necessary.

## WELDING STRESSES

It should be emphasised that the recommended values of preheat and heat input are based on low to moderate levels of restraint. For conditions of high restraint it is important to minimise the degree to which free contraction is hampered and it may be necessary to use higher preheats. Proper welding sequence and small joint configurations would be considered important in high restraint situations and it is advisable to establish welding parameters with simulated full scale weld tests.

Care should also be exercised at the assembly stage to avoid offset and angular distortion at the plate edge, undercutting and bad appearance.

## STRESS RELIEF

Stress relief may be conducted on BISALLOY® 60, 70, 80 and 80PV grades but is advisable only if absolutely necessary (eg. to comply with AS1210 in the case of road tankers). Stress relief is recommended within a 540 - 570°C temperature range for one hour per 25 mm of thickness. Thermal cycling is generally performed in accordance with AS1210 Code requirements for Q&T steels. The toes of weld beads should be dressed by grinding prior to any stress relief treatment in order to prevent stress relief cracking.

---

When stress relieving BISALLOY® steels ≤12 mm (typically 0.40 CE(IIW)) and matching strength across the weld is a requirement, it is recommended to weld with minimum permissible preheat/ interpass temperatures (Table 2) and heat input (Table 3) conditions to minimise the degree of softening or any loss of strength which may occur in the HAZ.

Consult Bisalloy Steels for further information if required.

## POST-WELD HEATING

Post-weld heating at 200 - 250°C may be conducted as an effective hydrogen dissolution treatment particularly when consumables other than H5 or H10 are used.





## HELPFUL HINTS

General rules for good quality welding of BISALLOY® steel:

- Use a low hydrogen process, eg. GMAW (MIG), FCAW (gas shielded)
- Adhere to the correct rules for storage and handling of low hydrogen consumables per the manufacturers' recommendations, or WTIA Tech. Note 3
- Clean joint area of all contaminants prior to welding
- Remove 1 - 2 mm from flame cut or gouged surfaces by grinding
- Select the recommended preheat, interpass and heat input parameters
- Position for downhand welding where possible
- Always use stringer beads, never wide weaves
- Use lower strength consumables on root runs and fillet welds (when the design permits)
- Use temper beads when necessary
- Arc strikes to be made in the joint preparation
- Particular attention should be given to tack welds re preheat, heat input and joint cleanliness requirements
- Grinding toes of fillet welds is particularly important in fatigue applications

## REFERENCES / FURTHER READING

- AS1554 Part 4 Welding of Q&T Steels
- AS1554 Part 5 Welding of Steel Structures Subject to High Levels of Fatigue Loading
- WTIA Technical Note 15
- WTIA Technical Note 3
- WTIA Technical Note 1

